

|   |   |
|---|---|
| <p>Product composition</p>  | <p>Characteristics</p> <p style="text-align: right;"><b>10</b></p>  |
| <p>Float</p> <p>Silicate</p>  | <ul style="list-style-type: none"> <li>▶ Cuttable with specialist equipment</li> <li>▶ Internal installation only</li> <li>▶ Double sided fire resistance</li> <li>▶ Excellent impact rating</li> <li>▶ Large tested sizes</li> <li>▶ EI30 - E60 applications</li> </ul>                              |
| <p>Technical characteristics</p>  | <p>Physical features</p>  |
| <ul style="list-style-type: none"> <li>▶ Fire classification: EI30</li> <li>▶ Impact classification: 1B1</li> <li>▶ Light transmission: 85%</li> <li>▶ Sound reduction: 38 dB</li> <li>▶ U value:</li> <li>▶ UV stability:</li> </ul> | <ul style="list-style-type: none"> <li>▶ Nominal Thickness: 15 mm</li> <li>▶ Thickness tolerances:</li> <li>▶ Dimensional tolerances:</li> <li>▶ Weight/m<sup>2</sup>: 37.6 kg</li> <li>▶ Temperature range:</li> <li>▶ Stock sheet size: 3100 x 2125 mm</li> <li>▶ Min manufactured size:</li> </ul> |
| <p>Possible applications</p>  |   |
| <p>Steel system</p> <p>Timber system</p>  | <p style="text-align: center;"> <b>F</b> L E X I B L E<br/> <b>I</b> N D E P E N D E N T<br/> <b>R</b> E S P O N S I V E<br/> <b>S</b> P E C I F I C<br/> <b>T</b> E C H N I C A L<br/> <b>FIRST IN FIRE GLASS</b> </p>   |
| <p style="text-align: right;">06/2015 <span style="margin-left: 100px;">37</span></p>   |   |

The diagrams in this document are for guidance purpose only, for actual projects specific drawings are required.